Fields of application

Wellness & living	electric blankets, electric pillows, electric carpet heating, underfloor

Physical properties

Density (kg/dm³)	8.3
Conductivity soft (MS / m)	3.4
Temp.coeff. of resistance (% / K)	0.01
Resistivity soft (Ω x mm² /m)	0.2941
Tensile strength soft (N / mm²)	450

Spool dimensions and filling weight

Type	Weight [kg]	Flange [mm]	Core [mm]	Bore [mm]	Inner size [mm]	Outer size [mm]
K 100	1.6	100	63	16	80	100
K 125	3.5	125	80	16	100	125
K 160	8	160	100	22	128	160
K 200	16	200	125	22	160	200
K 250	25	250	160	22	160	200
K 355	45	355	224	36	160	200
DWF 355	45	355	224	36	160	200