Fie	Fields of application By Selective Selectric blankets, electric pillows, electric carpet heating, underfloor							
B		Weight [kg]	Flange	Core	Bore	Inner size	Outer size [mm]	
	K 100	1.6	100	63	16	80	100	
be⁻	K 125	3.5	125	80	16	100	125	
	K 160	8	160	100	22	128	160	
Fi∈	K 200	16	200	125	22	160	200	
	K 250	25	250	160	22	160	200	
	K 355	45	355	224	36	160	200	
_	DWF 355	45	355	224	36	160	200	
	Further app		car seat heating, sport turf, heating, operating table heating, leakage detection, electrofusion applications					

Physical properties

Density (kg/dm³)	8.8
Conductivity soft (MS / m)	25.5
Temp.coeff. of resistance (% / K)	0.19
Resistivity soft ($\Omega \times mm^2/m$)	0.0392
Tensile strength soft (MPa)	350

Spool dimensions and filling weight

Туре	Weight [kg]	Flange [mm]	Core [mm]	Bore [mm]	Inner size [mm]	Outer size [mm]
K 100	1.6	100	63	16	80	100
K 125	3.5	125	80	16	100	125
K 160	8	160	100	22	128	160
K 200	16	200	125	22	160	200
K 250	25	250	160	22	160	200
K 355	45	355	224	36	160	200
DWF 355	45	355	224	36	160	200
DWF 355	45	355	224	36	160	200