

Fields of application

Physical properties and filling weight

Wellness & living electric blankets, electric pillows, electric carpet heating, underfloor

Typ	Füllgewicht [max. kg]	Flansch [mm]	Kern [mm]	Bohrung [mm]	Innenmaß [mm]	Außenmaß [mm]
K 100	1.6	100	63	16	80	100
K 125	3.5	125	80	16	100	125
K 160	8	160	100	22	128	160
K 200	16	200	125	22	160	200
K 250	25	250	160	22	160	200
K 355	45	355	224	36	160	200
DWF 355	45	355	224	36	160	200
Further applications		car seat heating, sport turf, heating, operating table heating, leakage detection, electrofusion applications				

Physical properties

Density (kg/dm ³)	8.5
Conductivity soft (MS / m)	16
Temp.coeff. of resistance (% / K)	0.15
Resistivity soft (Ω x mm ² / m)	0.0625
Tensile strength soft (MPa)	500

Spool dimensions and filling weight

Typ	Füllgewicht [max. kg]	Flansch [mm]	Kern [mm]	Bohrung [mm]	Innenmaß [mm]	Außenmaß [mm]
K 100	1.6	100	63	16	80	100
K 125	3.5	125	80	16	100	125
K 160	8	160	100	22	128	160
K 200	16	200	125	22	160	200
K 250	25	250	160	22	160	200
K 355	45	355	224	36	160	200
DWF 355	45	355	224	36	160	200

