B	Туре	Weight [kg]	Flange [mm]	Core [mm]	Bore [mm]	Inner size [mm]	Outer size [mm]
	K 100	1.6	100	63	16	80	100
ber	K 125	3.5	125	80	16	100	125
	K 160	8	160	100	22	128	160
Fi	K 200	16	200	125	22	160	200
	K 250	25	250	160	22	160	200
	K 355	45	355	224	36	160	200
	DWF 355	· 45	355	224	36	160	200

Physical properties

Density (kg/dm³)	8.7
Conductivity hard (MS / m)	4.9
Conductivity soft (MS / m)	5.1
Temp.coeff. of resistance (% / K)	0.0357
Resistivity hard ($\Omega \ x \ mm^2 \ /m$)	0.2041
Resistivity soft ($\Omega \times mm^2 /m$)	0.1961
Tensile strength hard (N / mm²)	1000
Tensile strength soft (N / mm²)	420

Spool dimensions and filling weight