

bedra electronic wire CuAg0.5Zn1 out of a highly conductive alloy for various applications (ribbons, heating conductors / resistance wire, special cables, bobbins, connectors, etc.).

Standardization and composition

DIN	not standardized
Alloy composition	Average values (%)
Cu	balance
Zn	1.0
Ag	0.5
Others	max. 0.5

Physical properties

Density (kg/dm³)	8.9
Melting range (°C)	1060 - 1085
E-Modulus (kN/mm²)	125
Thermal conductivity (W / m x K)	295
Coefficient of linear mean expansion (10-6/K)	17.8
Electric conductivity (m / Ω x mm²)	45 - 47
Electric conductivity (IACS %)	~ 77 - 80
Resistivity (Ω x mm² / m)	0.0213 - 0.0222