

bedra electronic wire Ms70 out of a brass alloy for various applications (ribbons, heating conductors / resistance wire, special cables, bobbins, connectors, etc.).

## Standardization and composition

<b>Norm</b>	CuZn30
<b>DIN</b>	17660
<b>EN DIN12166</b>	CW 505 L
<b>CDA UNS</b>	260
<b>Alloy composition</b>	Average values according to standard (%)
<b>Cu</b>	70.0
<b>Zn</b>	balance
<b>Others</b>	max. 0.5

## Physical properties

<b>Density (kg/dm<sup>3</sup>)</b>	8.5
<b>Melting range (°C)</b>	910 - 965
<b>E-Modulus (kN/mm<sup>2</sup>)</b>	114
<b>Thermal conductivity (W / m x K)</b>	126
<b>Coefficient of linear mean expansion (10-6/K)</b>	19.8
<b>Electric conductivity (m / Ω x mm<sup>2</sup>)</b>	15.5 - 16.5
<b>Electric conductivity (IACS %)</b>	~ 26 - 28
<b>Resistivity (Ω x mm<sup>2</sup> / m)</b>	0.0606 - 0.0645