

bedra 15000

Material Designation *

UNS	C15000
EN	CuZr (CW 120 C)
JIS	/
GB	TZr0.15

Chemical Composition

Cu	Balance	%
Zr	0.1-0.2	%
Others	≤0.1	%



Characteristics

It has high electrical conductivity, thermal conductivity and good process performances.

Typical Application

It is applied for spot welding electrode and electrode cap, especially suitable for coating sheet. It is also suitable for components of electronic devices.

Physical Properties

Density ^①	8.9	g/cm ³
Electrical conductivity ^①	86	%IACS
Thermal conductivity ^①	367	W/(m·K)
Coefficient of thermal expansion ^②	17.0	10 ⁻⁶ / K
Modulus of elasticity	129	GPa

Note①: Temperature for testing is 20°C.

Note②: Temperature range for testing is 20-300°C.

Fabrication Properties

Cold workability	Excellent
Hot workability	Excellent
Brazing	Good
Resistance welding	Not recommended
Machinability compared with C36000	20%

Mechanical Properties

Diameter	Temper	Tensile Strength	Yield Strength	Elongation
mm		MPa min.	MPa min.	% min.
4 < Φ ≤ 25	R350	350	260	12
25 < Φ ≤ 50	R280	280	210	15

bedra 15000

Tolerance and Delivery Form

Straight Bar

Diameter	Tolerance ^③	Ovality	Length	Straightness
mm	mm	mm max.	mm max.	mm/m max.
5 ≤ Φ ≤ 6	0.06	0.03	4000	1.0
6 < Φ ≤ 10	0.10	0.05	4000	1.0
10 < Φ ≤ 20	0.16	0.08	4000	1.0
20 < Φ ≤ 25	0.18	0.09	4000	1.0
25 < Φ ≤ 30	0.20	0.10	4000	1.0
30 < Φ ≤ 40	0.24	0.12	4000	1.0
40 < Φ ≤ 42.5	0.30	0.15	4000	1.0

Note^③: The tolerances listed in the table are specified as all plus or all minus. When tolerances are specified as plus and minus (±), half the values given.

Composition	BSEN 12163-2016
Conductivity	BSEN 12163-2016
Mechanical Properties	BSEN 12163-2016
Fabrication Properties	CDA
Other Physical Properties	CDA

The datasheet is for your general information only and is not subject to revision. No claim can be derived from it unless is evidence of intent or gross negligence. The data given is with reference to the relevant standards as ASTM, BS EN, JIS, RWMA, SAE and is for reference only, no warranty can be derived from the data provided. The given info may not replace the customers' own tests.