

Brass

bedra 28500

Material Designation*

UNS	C28500
EN	CuZn42 (CW 510 L)
JIS	/
GB	H59

Chemical Composition

Cu	57.0-59.0	%
Pb	≤0.1	%
Sn	≤0.3	%
Al	≤0.05	%
Fe	≤0.3	%
Ni	≤0.3	%
Others	≤0.2	%
Zn	Balance	%

Characteristics

It has high strength, excellent hot working performance and good cold working performance. And it has good pressure machining and cutting performance, good brazability and weldability and good corrosion resistance.

Physical Properties

Density ^①	8.4	g/cm ³
Electrical conductivity ^①	≥20	%IACS
Thermal conductivity ^①	113	W/(m·K)
Coefficient of thermal expansion ^②	20.5	10 ⁻⁶ / K
Modulus of elasticity	105	GPa

Note①: Temperature for testing is 20°C.

Note②: Temperature range for testing is 20-300°C.



Typical Applications

It can be applied for all deep drawing and bending manufacturing stressed parts, such as pin, rivet, washer, nut, conduit, barometer spring, screen, radiator parts, etc.

Fabrication Properties

Cold workability	Fair
Hot workability	Excellent
Brazing	Excellent
Resistance welding	Good
Hot forging compared with C37700	100%
Machinability compared with C36000	60%

bedra 28500

Mechanical Properties

Diameter	Temper	Tensile Strength	Yield Strength	Elongation		
				MPa min.	MPa min.	A ₁₀₀ % min.
mm						
6 ≤ Φ < 80	R360	360	320(max)	--	15	20
2 ≤ Φ < 40	R430	430	220	6	8	10
2 ≤ Φ < 14	R500	500	350	--	3	5

Tolerance and Delivery Form

Straight Bar

Diameter	Tolerance ^③	Ovality	Length		Straightness
			mm max.	ft max.	
mm	mm	mm			mm/m max.
2 ≤ Φ < 3	0.03	0.0075	2500	8.2	1.0
3 ≤ Φ < 6	0.04	0.01	2500	8.2	0.5
6 ≤ Φ < 10	0.06	0.015	4000	13.1	0.5
10 ≤ Φ < 18	0.08	0.02	4000	13.1	0.5
18 ≤ Φ < 25	0.12	0.03	4000	13.1	0.5
25 ≤ Φ < 40	0.20	0.05	4000	13.1	0.5
40 ≤ Φ < 60	0.30	0.075	4000	13.1	0.5
60 ≤ Φ < 80	0.60	0.15	3000	9.8	3.0
80 ≤ Φ < 100	1.60	0.40	2000	6.6	5.0
100 ≤ Φ ≤ 120	2.00	0.50	1500	4.9	6.0

Note^③: The tolerances listed in the table are specified as all plus or all minus. When tolerances are specified as plus and minus (±), half the values given.

*Composition
Conductivity
Mechanical Properties
Fabrication Properties
Other Physical Properties

BS EN 12164-2016, (Pb, for reference only.)
For reference only
BS EN 12164-2016
CDA
CDA, Elastic modulus for reference only.

The datasheet is for your general information only and is not subject to revision. No claim can be derived from it unless is evidence of intent or gross negligence. The data given is with reference to the relevant standards as ASTM, BS EN, JIS, RWMA, SAE and is for reference only, no warranty can be derived from the data provided. The given info may not replace the customers' own tests.