

bedra 49260

Material Designation *

UNS	C49260
EN	/
JIS	/
GB	HBi60-1-0.05

Chemical Composition

Cu	58.0-63.0	%
Pb	≤ 0.009	%
Bi	0.50-1.8	%
P	0.05-0.15	%
Fe	≤ 0.5	%
Sn	≤ 0.5	%
Si	≤ 0.1	%
Cd	≤ 0.001	%
Zn	≤ Balance	%



Characteristics

Through replacing lead element by bismuth, it is not only ensuring the cutting performance of material but also environmental-friendly. It has excellent mechanical and electrical properties and it is one of the ideal substitute material for leaded brass.

Typical Applications

The alloy is widely used in TWS earphones, as well as used in CMOS lens products, electronics, hardware, machinery, connectors, valve core and food machinery industries.

Physical Properties

Density ^①	8.33	g/cm ³
Electrical conductivity ^①	21.7	%IACS
Thermal conductivity ^①	79	W/(m·K)
Coefficient of thermal expansion ^②	17.5	10 ⁻⁶ / K
Modulus of elasticity	108.9	GPa

Note^①: Temperature for testing is 20°C.

Note^②: Temperature range for testing is 20-300°C.

Fabrication Properties

Cold workability	Fair
Hot workability	Fair
Brazing	Good
Hot forging compared with C37700	70%
Machinability compared with C36000	90%

bedra 49260

Mechanical Properties

Diameter	Temper	Tensile Strength	Yield Strength	Elongation
mm		MPa min.	MPa min.	% min.
3 ≤ Φ < 12	H02	395	170	7
12 ≤ Φ < 25	H02	380	170	10
25 ≤ Φ < 50	H02	345	140	15
50 ≤ Φ ≤ 80	H02	310	105	20

Tolerance and Delivery Form

Diameter	Tolerance ^③	Ovality	Straight Bar		Straightness
			Length		
mm	mm	mm	mm max.	ft max.	mm/m max.
3 ≤ Φ < 6	0.02	0.01	4000	13.1	0.5
6 ≤ Φ < 10	0.03	0.015	4000	13.1	0.5
10 ≤ Φ < 18	0.04	0.02	4000	13.1	0.5
18 ≤ Φ < 30	0.06	0.03	4000	13.1	0.5
30 ≤ Φ < 50	0.10	0.05	4000	13.1	0.5
50 ≤ Φ < 60	0.15	0.075	4000	13.1	0.5
60 ≤ Φ < 80	0.30	0.15	3000	10.0	2.0

Note^③: The tolerances listed in the table are specified as all plus or all minus. When tolerances are specified as plus and minus (±), half the values given.

*Composition ASTM B974-2016a, Pb, for reference only.
 Conductivity ASTM B974-2016a
 Mechanical Properties ASTM B974-2016a
 Fabrication Properties CDA
 Other Physical Properties CDA

The datasheet is for your general information only and is not subject to revision. No claim can be derived from it unless is evidence of intent or gross negligence. The data given is with reference to the relevant standards as ASTM, BS EN, JIS, RWMA, SAE and is for reference only, no warranty can be derived from the data provided. The given info may not replace the customers' own tests.