

Manganese Brass

bedra 67300

Material Designation *

UNS	C67300
EN	/
JIS	/
GB	HMn60-3-1.7-1

Chemical Composition

Cu	58-63	%
Mn	2.0-3.5	%
Pb	0.4-3.0	%
Si	0.5-1.5	%
Al	≤0.25	%
Sn	≤0.3	%
Fe	≤0.5	%
Ni	≤0.25	%
Zn	Balance	%



Characteristics

The alloy is a copper-zinc-manganese-silicon-lead series copper-based multi-element ($\alpha+\beta$) two-phase alloy. The addition of silicon and manganese improves the strength and wear resistance of the alloy, and the addition of lead enhances its wear resistance and machinability.

It is a copper alloy with high strength and high wear resistance.

Physical Properties

Density ^①	8.3	g/cm ³
Melting point	873.9	°C
Electrical conductivity ^①	22	%IACS
Thermal conductivity ^①	95	W/(m·K)
Coefficient of thermal expansion ^②	19.1	10 ⁻⁶ /K
Modulus of elasticity	117.2	GPa

Note^①: Temperature for testing is 20°C.

Note^②: Temperature range for testing is 20-300°C.

Typical Applications

It is used in bushings, main plates, sub-plates, bearings and shafts for the hydraulic industry and wear-resistant parts such as sleeves and turbines.

Fabrication Properties

Cold workability	Fair
Hot workability	Excellent
Brazing	Good
Resistance welding	Not recommended
Hot workability compared with C37700	100%
Machinability compared with C36000	70%

Manganese Brass

bedra 67300

Mechanical Properties

Diameter	Temper	Tensile Strength	Yield Strength	Elongation	Hardness
mm		MPa min.	MPa min.	% min.	HB min.
$\Phi \leq 25$	H02	448	275	12	70
$25 < \Phi \leq 75$	H02	399	241	15	70
$75 < \Phi \leq 120$	H02	379	206	18	65

Tolerance and Delivery Form

Straight Bar				
Diameter	Tolerance ^③	Ovality	Length	Straightness
mm	mm	mm	mm max.	mm/m max.
$6 \leq \Phi < 10$	0.06	0.03	4000	0.3
$10 \leq \Phi < 18$	0.07	0.03	4000	0.3
$18 \leq \Phi < 30$	0.08	0.04	4000	0.5
$30 \leq \Phi < 50$	0.16	0.08	4000	0.5
$50 \leq \Phi < 60$	0.80	0.40	4000	1.0
$60 \leq \Phi < 80$	1.60	0.80	3000	1.0
$80 \leq \Phi \leq 120$	2.00	1.00	2500	5.0

Note^③: The tolerances listed in the table are specified as all plus or all minus. When tolerances are specified as plus and minus (\pm), half the values given.

*Composition SAE J463
 Conductivity CDA
 Mechanical Properties SAE J463
 Fabrication Properties CDA
 Other Physical Properties CDA

The datasheet is for your general information only and is not subject to revision. No claim can be derived from it unless is evidence of intent or gross negligence. The data given is with reference to the relevant standards as ASTM, BS EN, JIS, RWMA, SAE and is for reference only, no warranty can be derived from the data provided. The given info may not replace the customers' own tests.